

COMPOSITION FOR CATIONIC ELECTRODEPOSITION COATING

Patent number: JP61115974
Publication date: 1986-06-03
Inventor: NISHIJIMA KANJI; others: 01
Applicant: NIPPON PAINT CO LTD
Classification:
- International: C09D5/44; C09D3/48
- european:
Application number: JP19840237123 19841109
Priority number(s):

Abstract of JP61115974

PURPOSE: To provide the titled compsn. consisting of a reaction product between a dimer-modified polyepoxide and another type of a cationic resin and forming an electrodeposition coating film which has no crater and has high flexibility and strong (secondary) adhesion.

CONSTITUTION: A dimer acid-modified polyepoxide (a) with an epoxy equivalent of 500-5,000 (e.g. polyglycidyl ether or polypropylene glycol) is prepared by addition reaction of a dimer acid obtained by polymerizing an unsatd. fatty acid, with a polyvalkyene glycol polyepoxide in an equivalent ratio of 1.5-2.5/1. Then (a) is made to react with (b) polyoxvalkyene polyamide having an amine equivalent of 55-70 (e.g. polyoxypropylenediamine) in such amts. that the equivalent ratio of the epoxide group in (a) to the amine group in (b) is 1/1.15-1.60. The compsn. is obtained by blending 2-40wt% resulting reaction product with 98-60wt% another type of cationic resin.

Data supplied from the **esp@cenet** database - Worldwide